



**Product name** : **MoTip Industrial Zinc Repair Spray**  
**Article number** : **07304**

**Supplier / Producer** : **MOTIP DUPLI B.V.**  
**Wolframweg 2**  
**NL-8471 XC WOLVEGA**

---

## Product description

High quality zinc repair spray to repair minor damage in surfaces of steel galvanised by immersion.

## Product characteristics

Fast drying  
Good coverage  
Non-fading and UV resistant  
Good surface hardness  
Resistant to petrol, chemicals and weather influences  
Wear resistant and scratch free  
Excellent adhesion

## Physical and Chemical Characteristics

Contents : 500 ml  
Base : Nitro-cellulose binder  
Colour : Silver  
VOC-content : Approximately 93% w/w  
Solid content : Approximately 7% w/w  
Coverage : 1,5 to 2 m<sup>2</sup>  
Dust dry : After 5 to 10 minutes  
Tack free : After 10 to 20 minutes  
Hardened/re-sprayable : After 2 hours  
Heat resistant : To 110°C

## Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

### Pre Treatment

The surface should be clean, dry and free of grease.

### Treatment

The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the zinc repair spray in several thin layers. Before applying the next layer, again shake the aerosol..

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**